

Non JIS material definition is listed on P.1351 - 1352










- Since hardness of nitrided layer is high and coefficient of friction is extremely low as 0.05~0.12, abrasion resistance, corrosion resistance and burning resistance are improved.
- Since nitrided layer is about 5  $\mu$ , process surface other than sliding surface for alteration or adjustment.



Though there is nitrided layer all over, avoid processing (polishing) any part used as sliding surface during use.

\*Not to eliminate nitrided layer, process (polish) surface other than the

sliding surface as shown in the left figure.